

DENTAL RESIN

Dental LT Clear (V2)

Biocompatible Photopolymer Resin for Form 2 and Form 3B

Directly print affordable, high-quality occlusal splints in-house with Dental LT Clear Resin (V2). Highly durable and resistant to fracture, this color-corrected material prints clear, polishes to high optical transparency, and resists discoloration over time for a finished appliance you'll be proud to deliver.

Occlusal guards

Splints



FLDLCL02

formlabs 

Prepared 06 . 09 . 2020
Rev 01 06 . 09 . 2020

To the best of our knowledge the information contained herein is accurate. However, Formlabs, Inc. makes no warranty, expressed or implied, regarding the accuracy of these results to be obtained from the use thereof.

DENTAL LT CLEAR RESIN (V2) MATERIAL PROPERTIES DATA

	METRIC	IMPERIAL	
Mechanical Properties	Post-Cured ^{1,2}	Post-Cured ^{1,2}	Method
Elongation	12%	12%	ASTM D638-10 (Type IV)
Flexural Strength at 5% Strain	84 MPa	12.2 ksi	ASTM D790-15 (Method B)
Flexural Modulus	2300 MPa	332 ksi	ASTM D790-15 (Method B)
Hardness Shore D	78 D	78 D	ASTM D2240-15 (Type D)

Dental LT Clear Resin (V2) has been evaluated in accordance with ISO 10993-1:2018, *Biological evaluation of medical devices - Part 1: Evaluation and testing within a risk management process*, and ISO 7405:2018, *Dentistry - Evaluation of biocompatibility of medical devices used in dentistry*, and passed the requirements for the following biocompatibility risks:

ISO Standard	Description ³
EN ISO 10993-5:2009	Not cytotoxic
ISO 10993-10:2010/(R)2014	Not an irritant
ISO 10993-10:2010/(R)2014	Not a sensitizer
ISO 10993-11:2017	Not toxic
ISO 10993-3:2014	Not genotoxic

The product was developed and is in compliance with the following ISO Standards:

ISO Standard	Description
EN ISO 13485:2016	Medical Devices – Quality Management Systems – Requirements for Regulatory Purposes
EN ISO 14971:2012	Medical Devices – Application of Risk Management to Medical Devices

¹ Material properties may vary based on part geometry, print orientation, print settings, temperature, and disinfection or sterilization methods used.

² Data were measured on post-cured samples printed on a Form 3B printer with 100 µm Dental LT Clear Resin (V2) settings, washed in a Form Wash for 20 minutes in 99% Isopropyl Alcohol, and post-cured at 60°C for 60 minutes in a Form Cure.

³ Dental LT Clear Resin (V2) was tested at NAMS World Headquarters, OH, USA.