



Origin DM100™

Beige dental model resin with optional compination of strength, impact resistance, and dimensional stability.

General Properties	Norm	Typical Values
Appearance	—	Beige
Viscosity, 25°C	Cone/Plate Rheometer	750 cP
Density (liquid resin)	ASTM D4052-18a	1.12 g/cm ³

Tensile Properties	Norm	Typical Values
E Modulus	ASTM D638	2000 MPa
Ultimate Tensile Strength	ASTM D638	70 MPa
Elongation at Break	ASTM D638	5%

Impact Properties	Norm	Typical Values
Notched Izod, 23°C	ASTM D256	10 J/m

Hardness	Norm	Typical Values
Shore D	ASTM D2240	80

Thermal Stability	Norm	Typical Values
HDT at 0.45 MPa	ASTM D648	54°C
HDT at 1.82 MPa	ASTM D648	45°C

© 2022 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Origin and P3 are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. PSS_P3_Origin DM100_A4_0422a

www.goengineer.com



3D PRINTER SALES
info@goengineer.com
800.688.3234

CONSUMABLES HELP
supplies@goengineer.com
855.470.0647

3D PRINTER SUPPORT
AMsupport@goengineer.com
855.470.0647